
Product Description

ELOTEX[®] FX2322 is a redispersible binder based on a copolymer of vinyl acetate and ethylene.

Protective colloid	Polyvinyl alcohol
Additives	Mineral anti-block agents
Plasticisers	none
Solvents	none
Film-forming agents	none

Specifications

Appearance	free-flowing, white powder
Bulk density	350 - 500 g/l
Residual moisture	maximum 1.0%
Ash TGA 1000°C	6.0% +/- 1.5%
pH value	6.0 – 9.0 (as a 10% dispersion in water)
Min. film building temp.	+ 0°C
Film properties	opaque, flexible

Application Areas

For modification of flexible, hydraulically and non-hydraulically curing systems.

Main application areas

- Particularly well suited for use in flexible sealing compounds, flexible tile adhesives and EIFS (Exterior Insulation Finishing Systems) adhesive and covering mortars
- Highly flexible redispersible powder with broad performance spectrum for cement containing systems

Key Properties

During processing

- Excellent rheology and workability
- Improved water retention capability
- Reduced water demand

In the cured state

- High final strengths
- Increased cohesive force (cohesion) and adhesive bond strength on different substrates
- Excellent adhesion to rigid polystyrene foam slabs and mineral wool slabs, particularly after wet storage
- Good plastic behaviour and excellent flexibility: the impact resistance and plasticity of the mortar are decisively improved
- Improved freeze-thaw cycling resistance
- Reduced cracking
- Reduced shrinkage tendency

Powder Processing

Elotex redispersible powders can be blended in all commercial positive mixers with other dry additives to produce finished products in powder form. Since Elotex redispersible powders exhibit thermoplastic behaviour, mixing times should be as short as possible, and significant temperature rise caused by strong shear forces should be avoided. All hydraulically and non-hydraulically curing dry mixtures with Elotex redispersible powder may be easily mixed with water before application.

For mixing finished products in powder form, one usually places the required amount of mixing water in a suitable vessel and add the powder mixture under agitation. Too intensive agitation of the mixture may result in unwanted air inclusion. Before application, one should allow the mixture to stand for a short time. Depending on the properties of the other additives, the standing time will be in the range of approx. 1-5 minutes.

Packaging and Storage

Standard packaging: 20 kg paper sacks with polyethylene liners.

Other types of packaging such as Big Bags or silo wagons are possible on request.

As a basic rule it is recommended to store Elotex powder in a dry location at temperatures below 25°C and to process within six months. Sacks that are stored under pressure, damaged or left open for an extended period tend to cause blocking of the powder.

Quality, Safety and Environment

Elotex powders are non-toxic and are unclassified according to Regulation 88/379/EEC. We recommend all individuals using Elotex powder, or coming in contact with it, to observe the separate Safety Data Sheets. Our safety specialists will be pleased to advise you regarding safety, health and environmental issues of our products. Elotex has been certified according to DIN EN ISO9001 and DIN EN ISO14001.

Product Liability

The above information and recommendations are based upon our experience and are offered merely for advice. They do not absolve the consumer from making his own tests. Elotex AG, their representatives or distributor organizations have no control over the conditions under which Elotex powders are transported, stored, handled or used. Responsibility for damage arising from the use of our products cannot be derived from the recommendations given. The observance of any intellectual property rights of third parties is the responsibility of the consumer in each case.

Technical information may not be passed on to any third party without our previous consent.

Other Information

Version	3 / 28.10.2009
Replaces version from	19.8.2005
Date of issue	16.12.2003

AkzoNobel Functional Chemicals
Elotex AG
Industriestrasse 17a, CH-6203 Sempach Station
T +41 41 469 69 69 F +41 41 469 69 00
contact.elotex@akzonobel.com
www.akzonobel.com/elotex

